

DESCRIPTION A black, open cell, specialized, polyether foam.

TYPICAL APPLICATIONS Shock absorption, cushioning and padding.
This moldable and very light foam has a soft feel.

<u>PHYSICAL PROPERTIES</u>	<u>TYPICAL VALUES</u>	<u>TEST METHODS</u>
Density kg/m ³ (lbs/ft ³)	23 – 27 (1.4 – 1.7)	DIN EN ISO 845
Tensile Strength (min)	100 kPa	DIN EN ISO 1798
Elongation (min)	300%	DIN EN ISO 1798
Compression Force @ 40% (min)	1.0 kPa	DIIN EN ISO 3386-1
Compression Set @ 50% (max)	25%	DIN EN ISO 1856
Pore Size (PPI)	40 – 65	Visual

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta foamtec, inc. at (800)438-0678.