

## DESCRIPTION

A reticulated, fully open pore, flexible polyester foam available in a wide range of colors.

## TYPICAL APPLICATIONS

P-100Z has extremely low resistance to air flow, unusually high particle collecting capacity, excellent high and low temperature resistance (up to 250° F for short time periods) excellent shelf life, chemical resistance, good workability and self-gasketing capabilities.

PHYSICAL PROPERTIESTYPICAL VALUESTEST METHODS

Density, (lbs./ft <sup>3</sup> )	1.90	ASTM D3574
IFD @25%	0.40 psi	ASTM D3574
@65%	0.65 psi	ASTM D3574
Tensile Strength	35 psi	ASTM D3574
Elongation	400%	ASTM D3574
Tear Strength	3.9 lb/in	ASTM D3574
50% Compression Set	12	ASTM D3574
Pore Size (ppi)	100	
Reticulation Method	Thermal	

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta foamtec, inc. at (800)438-0678.