

**DESCRIPTION**

A natural color, reticulated, very open cell, flexible polyester foam.

**TYPICAL APPLICATIONS**

Filtration and other applications requiring minimum restriction to air movement. This foam has low air resistance, low pressure-drop, large dust holding capacity; can be shaped, glued and sewn. It is washable, reusable and able to separate oil based materials in water.

**PHYSICAL PROPERTIES****TYPICAL VALUES****TEST METHODS**

Porosity, ppi	10	Visual
Density, #/cu ft	1.9	ASTM D-3574
Tensile Strength, psi	20	ASTM D-3574
Ultimate Elongation, %	200	ASTM D-3574
Tear Strength, #/in	5.5	ASTM D-3574
50% Compression Set	10	ASTM D-3574
Compression Deflection, psi @ 25%	0.5	ASTM D-3574
Pressure Drop, Inches of Water	.18	MIL-B-83054B

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta foamtec, inc. at (800)438-0678.