

DESCRIPTION	P-80Z is a reticulated, fully "open pore," flexible, ester type of polyurethane foam.
APPLICATION	Filtration, acoustic, de-misting, electronic system protection and other uses where a minimum restriction to airflow is required.
TYPICAL APPLICATIONS	Relatively low air resistance, low-pressure drop, large dust holding capacity and washable for reuse. Can be shaped, glued and sown.

<u>PHYSICAL PROPERTIES</u>	<u>TYPICAL VALUES</u>	<u>TEST METHODS</u>
Density (lbs/ft ³)	1.9	ASTM D3574
Compression Force Deflection @ 25% (lbs/in ²)	0.4	ASTM D3574
Tensile Strength (lbs/in ²)	35	ASTM D3574
Tear Resistance (lbs/in ²)	3.9	ASTM D3574
Ultimate Elongation (%)	300	ASTM D3574
Clickability	Good to Excellent	
Pores Per Inch	80	
Compression Set @ 50%	12	ASTM D3574

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta-foamtec, inc. at (800)438-0678.