

DESCRIPTION	An open cell, fire retardant, 2# density, polyester, polyurethane foam.
TYPICAL APPLICATIONS	Filtering, cushioning, insulation, sound absorption, gaskets and seals. This foam is odorless, breathable, fire retardant and resistant to bacteria.

<u>PHYSICAL PROPERTIES</u>	<u>TYPICAL VALUES</u>	<u>TEST METHODS</u>
Density, (lbs./ft <sup>3</sup> )	1.8 – 2.2	ASTM D-3574
CFD @ 25%	0.4	
@ 65%	0.74	ASTM D-3574
Tensile Strength, psi	15.0 min	ASTM D-3574
% Elongation	175.0 min	ASTM D-3574
Tear Strength, #/in	1.0 min	ASTM D-3574
Compression Set, 50% Deflection (%)	15.0 max	ASTM D-3574
Pore Size (PPI)	70 +/- 10	Visual
Fire Retardancy	Pass	UL94HF-1

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta foamtec, inc. at (800)438-0678.