

DESCRIPTION

RF2.5-900Z is a compressed, 90 PPI, flexible ester polyurethane reticulated foam. The foam has been compressed 2.5 to 1.

TYPICAL APPLICATIONS

Sound absorption, air and liquid filters, oil wicks and reservoirs, gaskets, ink pads, rollers, pressure pads and vibration mounts. This foam has strong physical strength, abrasion resistance and solvent resistance.

PHYSICAL PROPERTIESTYPICAL VALUESTEST METHODS

Density, pcf	4.0 – 5.0-Felted 1.7 – 2.1-Base Foam	ASTM D-3574
Tensile, psi	30	ASTM D-3574
% Elongation	50	ASTM D-3574
Compression Load Deflection, psi (25/65%)	.3 .45	ASTM D-3574
Compression Set, 50%	5.1	ASTM D-3574

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta foamtec, inc. at (800)438-0678.