

DESCRIPTION A soft, low density, black, closed-cell polyvinyl chloride foam.

TYPICAL APPLICATIONS Filler in cushioning, vibration damping, and sealing against air, moisture and dust. For automotive industry (in conformance with Chrysler MS-AY510 series) as well as in air conditioning industry, typically on galvanize metal substrates.

<u>PHYSICAL PROPERTIES</u>	<u>TYPICAL VALUES</u>	<u>TEST METHODS</u>
Density (lbs/cu ft)	7	
Hardness (Shore 00)	10	ASTM D-2240
Compression Deflection (psi)	0.7	ASTM D-1667
Compression Set (% loss from original height)	10	ASTM D-1667
Water Absorption (lbs/sq ft cut surface) % by volume	0.077/3.2	ASTM D-1667
Tensile Strength (psi)	20	ASTM D-412
Percent Elongation	150	ASTM D-412
Thermal Conductivity (BTU/in) (sq ft) (hr) (°F)	0.27	ASTM C-518

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta foamtec, inc. at (800)438-0678.