

DESCRIPTION An open cell, polyester, polyurethane foam. This foam is flexible, breathable, non-linting, very soft to the touch, odorless and wets out fast.

TYPICAL APPLICATIONS Retaining, transferring and absorbing liquids.

<u>PHYSICAL PROPERTIES</u>	<u>TYPICAL VALUES</u>	<u>TEST METHODS</u>
Density (lbs/ft ³)	1.8	ASTM 3574
Tensile Strength (PSI)	25 – Wet 30 – Dry	ASTM 3574
CFD (PSI) @ 25%	.56	ASTM 3574
@ 65%	.81	
Elongation %	480 – Wet 400 – Dry	ASTM 3574
Tear Strength (PLI)	4.2	ASTM 3574
Compression Set (%) @ 50%	11	ASTM 3574
Water-holding (X dry weight)	33	
Volume Swell (%)	3	
Wet Out	10 seconds	
Pore Size (PPI)	85	

The data and information above represents typical values that are generally accepted throughout the industry and appear in manufacturer's literature. Actual physical properties may vary by manufacturing lot. These values do not constitute a guarantee of performance, actual or implied. The suitability of this product may be application specific and should be determined prior to being specified.

For more information, contact pinta foamtec, inc. at (800)438-0678.